



## TECHNICAL PRODUCT INFORMATION

|                             |  |
|-----------------------------|--|
| <b>Product:</b>             | White Ground Cover (White/Black)   |
| <b>Product Description:</b> | Woven Polypropylene fabric. Light reflection formulated to resist UV degradation, and allow water, air and nutrients to Pass through the fabric. |
| <b>Weigh:</b>               | 3.2 oz   |
| <b>Width:</b>               | Up to 15' ft. (4.5 m)  |
| <b>Length:</b>              | According to customers order   |

### Product Properties

| Property              | Test Method | Units               | Minimum Average                       |
|-----------------------|-------------|---------------------|---------------------------------------|
| Material              |             |                     | Polypropylene                         |
| Color                 |             |                     | White with Black Strip every 12"      |
| Construction Weave    | ASTM D-5261 | OZ/SY (GSM)         | 3.2 (108)                             |
| Grab Tensile Strength | ASTM D-4632 | LBS                 | Warp 25<br>Welf 100                   |
| Grab Elongation       | ASTM D-4632 | %                   | Warp 25<br>Welf 22                    |
| Trapezoid Tear        | ASTM D-4533 | LBS                 | Warp 80<br>Welf 70                    |
| Puncture              | ASTM D-6241 | LBS                 | 500                                   |
| Water Permeability    | ASTM D-4491 | GAL/MIN/SF          | 15                                    |
| UV Exposure           | ASTM D-4355 | % Strength Retained | 70% After 2500 Hrs Xenon Arc Exposure |

All statements, information and data given herein are believed to be accurate and reliable, but are presented without guarantee and warranty or responsible any kind, express, or limited. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommended to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

